PRODUCT DATA SHEET

CORE – EI4012

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc; as per IEC standards

Effective parameters irrespective of material grade (per set)

Parameter	Value	Unit
Effective Length (L_e)	76.8	mm
Effective Area (A_e)	148.0	mm^2
Effective Area (A_{Min})	136.0	mm^2
Effective Volume (V_e)	11400	mm^3
Approx. Weight (without gap)	58.0	g/set

EI4012 Un-gapped (OL)
Test Conditions: 1kHz/1mT/CFR COIL,N=100/25˚C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_V (W/set)	Ordering code
CF139	2100 ±20%	3950 +30%/-20%	≤1.14 (100mT,100kHz,100^{0}C)	CF139 EI4012 OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value

Regd. Office & Works: Jabli, Distt. Solan, Himachal Pradesh – 173 209 (India)
E-mail: sales@cosmoferrites.com